

Cardolite® FormuLITE™ 2502A + 2401B

Liquid Epoxy System

Technical Datasheet

DESCRIPTION

Cardolite FormuLITE 2502A and FormuLITE 2401B are a two-component epoxy system recommended for the manufacturing of reinforced composites by wet lay-up, resin transfer molding (RTM), lamination and vacuum infusion. Both the epoxy resin and the amine hardener are based on components from renewable sources. The calculated bio-based content of the system is 27%.

PROPERTIES

PROPERTY	TYPICAL VALUES ¹	TEST METHOD
RESIN FormuLITE 2502A		
Appearance	Clear liquid	Visual
Color (Gardner)	≤ 1	ASTM D1544
Viscosity @ 25°C (cPs)	930	ASTM D2196
Density @ 25°C (kg/L) (lbs/gal)	1.13 9.47	ASTM D1475
Flash point	> 150°C / 302°F	ASTM D93
Shelf Life (Months)	12	-
HARDENER FormuLITE 2401B		
Appearance	Light Yellow Liquid	Visual
Color (Gardner)	≤ 8	ASTM D1544
Viscosity @ 25°C (cPs)	90	ASTM D2196
Density @ 25°C (kg/L) (lbs/gal)	0.95 7.93	ASTM D1475
Flash point	> 110°C / 230°F	ASTM D93
Shelf Life (Months)	12	-

¹Typical properties are not to be construed as specifications

RECOMMENDED PROCESSES

Epoxy-based composites:

- Wet lay-up
- Resin transfer molding (RTM)
- Laminates
- Vacuum infusion

ADVANTAGES

- Good processability
- Good wetting of carbon, glass and natural fibers
- Good mechanical and thermal properties
- Improved water, acid and alkali resistance
- Based on renewable raw material feedstock

TYPICAL PROCESSING DATA

PROPERTIES	TYPICAL VALUES	TEST METHOD
Mixing ratio by weight	100:33	-
Mixing ratio by volume	100:40	-
Mix viscosity @ 25°C (cPs)	480	ASTM D2196
Mix viscosity @ 40°C (cPs)	175	ASTM D2196
Pot life, 100 g mix @ 23°C (min)	125	Internal Method ²
Pot life, 100 g mix @ 40°C (min)	63	Internal Method ²
Peak exotherm, 100 g mix @ 23°C (°C)	31	ASTM 2471-99
Peak exotherm, 100 g mix @ 23°C (°C)	70	ASTM 2471-99

²Pot life is measured when the formulation reaches a limit viscosity of 10,000 cPs starting from the reference temperature.

TYPICAL CURED SYSTEM PROPERTIES

PROPERTIES	TYPICAL VALUES ³	TEST METHOD
Ultimate glass transition temperature ⁴ (°C)	88	ASTM 3418-99
Water absorption at 25°C (7/14 days)	0.43/0.59	ASTM D543
Alkali resistance - 10% sodium hydroxide at 25°C (7/14 days)	0.36/0.53	ASTM D543
Acid resistance - 3% sulfuric acid at 25°C (7/14 days)	1.03/1.38	ASTM D543
Tensile strength (MPa)	66	ASTM D638-10
Tensile modulus (MPa)	2,893	ASTM D638-10
Tensile elongation at Fmax (%)	3.4	ASTM D638-10
Tensile elongation at break (%)	3.4	ASTM D638-10
Flexural strength (MPa)	96	ISO 178
Flexural modulus (MPa)	2,484	ISO 178
Bio-based content (% wt.)	27.0%	Calculated

³Curing schedule: 4h@RT + 2h@100°C

⁴DSC scan from 0 to 200°C at 20°C/min, 2nd run

CURING AND POST CURING

Post-curing is advisable for ambient cured systems to reach their best mechanical and thermal properties. It is recommended that cure and post-cure conditions be evaluated based on the size and shape of the composite part. In the case of room temperature curing, some heat treatment at a minimum of 50°C (122°F) should be done before demolding.

MIXING INSTRUCTIONS

It is recommended that components be weighed carefully to prevent mixing inaccuracies, which can adversely affect the properties of the final product. Both components should be mixed thoroughly to ensure homogeneity. In case of air entrapment, appropriate quantities of air release additives can be used. Pot life decreases when large amounts of mixture are prepared due to the exothermic reaction. It is recommended to split large amounts of mixture into smaller containers.

REGULATORY STATUS

Please refer to the material safety data sheet (MSDS). Specific information regarding chemical inventory listing can be obtained from your local sales representative.

SAFETY PRECAUTIONS

Please refer to the material safety data sheet (MSDS). Copies of the MSDS can be requested on the Cardolite website or via your local sales representative.

STABILITY AND STORAGE

Cardolite epoxy resins and hardeners may absorb moisture and carbon dioxide when left in open containers, which could result in increased viscosity, discoloration, reduction of reactivity, and/or crystallization of the products. These products should be kept tightly sealed in their original containers when not in use, and stored in a cool, dry place. Some Cardolite epoxy resins might crystallize. This reversible, physical phenomena can be greatly avoided by storing the resin at temperatures not below 25°C.

CONTACT INFORMATION



<http://www.cardolite.com>

Cardolite Corporation
500 Doremus Avenue
Newark, NJ 07105
United States of
America

T: +1-973-344-5015

Cardolite Specialty
Chemicals Europe NV
Wijmenstraat 21K / 2
B-9030 Mariakerke
(Gent)
Belgium

T: +32 (0) 92658826

Cardolite Specialty Chemicals
India LLP
Plot No. IP-1 & IP-2, Mangalore
Special Economic Zone
Bajpe, Mangalore 574 142,
India

T: + 91 (0) 824 2888 300

Cardolite Chemical Zhuhai
Ltd.
1248 Ninth Shihua Road
Gaolan Port Economic Zone
Zhuhai, Guangdong 519050
P.R. China

T: +86-756-726-9066

DISCLAIMER & COPYRIGHT

All statements, technical information and recommendations contained herein are based on tests Cardolite believes to be reliable, but the accuracy or completeness thereof is not guaranteed. Actual test method procedures may differ from listed standards; major differences are noted. Limitation of liability and remedy: Purchase or use of these products constitutes an agreement with seller and manufacturer that, if the product proves to be defective or unsuitable, seller's and manufacturer's liability and the exclusive remedy, regardless of tort or contract theory or of incidental or consequential damages shall be to receive, at seller's or manufacturer's option, an equivalent quantity of replacement product or a refund of the purchase price. This datasheet is copyrighted to Cardolite Corporation and may be reproduced but not altered in any way.