

Cardolite® Ultra LITE 2009H

Epoxy Curing Agent

Preliminary Technical Datasheet

DESCRIPTION

Cardolite Ultra LITE 2009H is a very light color and low viscosity phenalkamine curing agent suitable for epoxy coating applications protecting concrete and metal substrates. Ultra LITE 2009H provides faster hardness development than Ultra LITE 2009 in addition to excellent cure and film properties. This product is designed primarily for floor topcoats and self-levelers due to its good mechanical properties, and gloss and color retention.

PROPERTIES

PROPERTY	SPECIFICATION	TEST METHOD
Color (Gardner)	≤ 2	ASTM D1544
Viscosity @ 25°C (cPs)	≤ 500	ASTM D2196
Amine Value (mg KOH/g)	335 - 375	ASTM D2074

PROPERTY	TYPICAL VALUE	TEST METHOD
Appearance	Clear liquid	Visual
Theoretical Active Hydrogen Equivalent (AHEW) ¹	95	Calculated
Density @ 25°C (kg/L) (lbs/gal)	1.03 8.60	ASTM D1475
Flash Point	101.3°C / 214.3°F	ASTM D93
Recommended Use Level (phr, EEW 190)	50	-

Typical properties are not to be construed as specifications

¹Based on total product weight

APPLICATIONS

Cardolite Ultra LITE 2009H is usable in high solids coatings over concrete, primers, and metal substrates. This product's very low viscosity gives it good wetting and leveling properties, and its excellent yellowing resistance makes it ideal for topcoat applications. Its ability to cure over a wide temperature range and non-critical mix ratio can bring coatings broad application latitude. A durable, high performance, compatible barrier protection system for concrete can be formulated using this product in a topcoat or self-leveling coating over a surface primer based on another Cardolite phenalkamine, such as Cardolite NC-558, NX-2003, NX-5198, or NX-5454.

ADVANTAGES

- Excellent combination of fast cure and good pot-life at both ambient and low (>5°C/40°F) temperatures
- Good wetting and adhesion
- Excellent leveling properties
- Very good chemical resistance
- Compatible with most epoxy resins, solvents and their blends
- Excellent color and gloss retention
- Non-critical mix ratio
- No induction time required
- Non-toxic and non-corrosive
- Based from natural, renewable, non-food chain raw material feedstock

CURE PROPERTIES

	FORMULATION	TEST METHOD
Liquid Epoxy Resin (pbw, EEW 190)	100	
Cardolite Ultra LITE 2009H (pbw)	50	
Mix viscosity @ 25°C (cPs)	1,300	
Gel time, 50 g @ 25°C (min)	29	NTM-15
Thin film dry times, 8 mils (200 micron)		
@ 25°C (77°F) (hrs hard/through)	5.0/6.5	ASTM D5895
Film appearance @ 10°C, 92% RH	Slight haze	Visual

REGULATORY STATUS

Please refer to the material safety data sheet (MSDS). Specific information regarding chemical inventory listing can be obtained from your local sales representative.

SAFETY PRECAUTIONS

Please refer to the material safety data sheet (MSDS). Copies of the MSDS can be requested on the Cardolite website or via your local sales representative.

STABILITY AND STORAGE

Cardolite products may absorb moisture and carbon dioxide when left in open containers, which could result in increased viscosity, discoloration, reduction of reactivity, and/or crystallization of the products. These products should be kept tightly sealed in their original containers when not in use, and stored in a cool, dry place.

CONTACT INFORMATION



<http://www.cardolite.com>

Cardolite Corporation
11 Deer Park Drive
Suite 124
Monmouth Junction, NJ
08852
United States of America

Cardolite Specialty
Chemicals Europe NV
Wijmenstraat 21K / 2
B-9030 Mariakerke (Gent)
Belgium

Cardolite Specialty Chemicals
India LLP
Plot No. IP-1 & IP-2, Mangalore
Special Economic Zone
Bajpe, Mangalore 574 142
India

Cardolite Chemical
Zhuhai Ltd.
Biyang Road
Harbor Industrial Zone
Zhuhai, Guangdong 519050
P.R. China

T: +1-973-344-5015

T: +32 (0) 92658826

T: + 91 (0) 824 2888 300

T: +86-756-726-9066

DISCLAIMER & COPYRIGHT

All statements, technical information and recommendations contained herein are based on tests Cardolite believes to be reliable, but the accuracy or completeness thereof is not guaranteed. Actual test method procedures may differ from listed standards; major differences are noted. Limitation of liability and remedy: Purchase or use of these products constitutes an agreement with seller and manufacturer that, if the product proves to be defective or unsuitable, seller's and manufacturer's liability and the exclusive remedy, regardless of tort or contract theory or of incidental or consequential damages shall be to receive, at seller's or manufacturer's option, an equivalent quantity of replacement product or a refund of the purchase price. This datasheet is copyrighted to Cardolite Corporation and may be reproduced but not altered in any way.