DESCRIPTION


Cardolite GX-9006 is a novolac polyol based on cashew nutshell liquid technology.

TYPICAL PROPERTIES

PROPERTY	TYPICAL VALUE ¹	TEST METHOD
Appearance	Reddish liquid	Visual
Color (Gardner)	15	ASTM D1544
Viscosity @ 25°C (cPs)	2000 - 4000	ASTM D2196
Hydroxyl Value (mg KOH/g)	185 - 225	ASTM D4274
Water content (%)	≤ 0.1	Karl-Fischer

¹Typical properties are not to be construed as specifications

VISCOSITY PROFILE



¹Typical properties: not to be construed as specifications

Please refer to the material safety data sheet (MSDS). Specific information regarding chemical inventory listing can be obtained from your local sales representative.

SAFETY PRECAUTIONS

Please refer to the material safety data sheet (MSDS). Copies of the MSDS can be requested on the Cardolite website or via your local sales representative.

STABILITY AND STORAGE

Cardolite products will absorb moisture and carbon dioxide when left in open containers, which may result in increased viscosity, discoloration, reduction of reactivity, and/or crystallization of the products. These products should be kept tightly sealed in their original containers when not in use, and stored in a cool, dry place.

CONTACT INFORMATION



Cardolite Corporation 500 Doremus Avenue Newark, NJ 07105 United States of America Cardolite Specialty Chemicals Europe NV Wijmenstraat 21K / 2 B-9030 Mariakerke (Gent) Belgium

T: +32 (0) 92658826

Cardolite Specialty Chemicals India Pvt. Ltd. Plot No. IP-1 & IP-2, Mangalore Special Economic Zone Bajpe, Mangalore 574 142, India T: + 91 (0) 824 2888 300 http://www.cardolite.com

Cardolite Chemical Zhuhai Ltd. Biyang Road Harbor Industrial Zone Zhuhai, Guangdong 519050 P.R. China

T: +86-756-726-9066

T: +1-973-344-5015

DISCLAIMER & COPYRIGHT

All statements, technical information and recommendations contained herein are based on tests Cardolite believes to be reliable, but the accuracy or completeness thereof is not guaranteed. Actual test method procedures may differ from listed standards; major differences are noted. Limitation of liability and remedy: Purchase or use of these products constitutes an agreement with seller and manufacturer that, if the product proves to be defective or unsuitable, seller's and manufacturer's liability and the exclusive remedy, regardless of tort or contract theory or of incidental or consequential damages shall be to receive, at seller's or manufacturer's option, an equivalent quantity of replacement product or a refund of the purchase price. This datasheet is copyrighted to Cardolite Corporation and may be reproduced but not altered in any way.