

Cardolite® NX-1045

Brown Friction Particle

Technical Datasheet

DESCRIPTION

Cardolite NX-1045 is a brown granular, free flowing, cured solid resin derived from cashew nutshell liquid.

PROPERTIES

PROPERTY	SPECIFICATION	TEST METHOD
Acetone Extraction (%)	≤ 5	NTM 2
Ash (%)	3 - 6%	NTM 3
Volatile Loss @ 370°C / 698° F (%)	≤ 25	NTM 1
Moisture (%)	≤ 1	NTM 5
Screen Analysis, % residual		NTM 4
On U.S. standard sieve #40 (425 µm)	≤ 1	
On U.S. standard sieve #100 (150 µm)	50 - 70	
Through U.S. standard sieve #100	30 - 50	

PROPERTY	TYPICAL VALUE	TEST METHOD
Shelf Life (Years)	2	-

Typical properties are not to be construed as specifications

APPLICATIONS

Cardolite NX-1045 is a modified brown friction particle suitable for higher end disc pad and drum lining applications. This grade will improve pre-burnish friction and will help stabilizing the friction coefficient in the 200°C to 350°C temperature range.

ADVANTAGES

- Friction stabilizer in normal applications
- Reduces wear
- Increases pad hardness for higher performance
- Medium temperature stability

REGULATORY STATUS

Please refer to the material safety data sheet (MSDS). Specific information regarding chemical inventory listing can be obtained from your local sales representative.

SAFETY PRECAUTIONS

Please refer to the material safety data sheet (MSDS). Copies of the MSDS can be requested on the Cardolite website or via your local sales representative.

STABILITY AND STORAGE

Product packaging should be kept tightly closed when not in use, and the material stored in a cool, dry place.

CONTACT INFORMATION



<http://www.cardolite.com>

Cardolite Corporation
500 Doremus Avenue
Newark, NJ 07105
United States of America

T: +1-973-344-5015

Cardolite Specialty
Chemicals Europe NV
Wijmenstraat 21K / 2
B-9030 Mariakerke (Gent)
Belgium

T: +32 (0) 92658826

Cardolite Specialty Chemicals
India Pvt. Ltd.
Plot No. IP-1 & IP-2, Mangalore
Special Economic Zone
Bajpe, Mangalore 574 142,
India

T: + 91 (0) 824 4289 777

Cardolite Chemical Zhuhai Ltd.
Biyang Road
Harbor Industrial Zone
Zhuhai, Guangdong 519050
P.R. China

T: +86-756-726-9066

DISCLAIMER & COPYRIGHT

All statements, technical information and recommendations contained herein are based on tests Cardolite believes to be reliable, but the accuracy or completeness thereof is not guaranteed. Actual test method procedures may differ from listed standards; major differences are noted. Limitation of liability and remedy: Purchase or use of these products constitutes an agreement with seller and manufacturer that, if the product proves to be defective or unsuitable, seller's and manufacturer's liability and the exclusive remedy, regardless of tort or contract theory or of incidental or consequential damages shall be to receive, at seller's or manufacturer's option, an equivalent quantity of replacement product or a refund of the purchase price. This datasheet is copyrighted to Cardolite Corporation and may be reproduced but not altered in any way.