

Cardolite[®] NX-5110

Epoxy Curing Agent

Preliminary Technical Datasheet

DESCRIPTION

Cardolite NX-5110 is an epoxy curing agent based on latest modified phenalkamine technology.

TYPICAL PROPERTIES

PROPERTY	TYPICAL VALUE	TEST METHOD
Appearance	Yellow Liquid	Visual
Color (Gardner)	≤ 8	ASTM D1544
Viscosity @ 25°C (cPs)	2,000 - 3,750	ASTM D2196
Amine Value (mg KOH/g)	230 - 255	ASTM D2074
Theoretical Active Hydrogen Equivalent (AHEW) ¹	165	Calculated
Solids (% by weight)	78 - 82	ASTM D2369-98
Density @ 25°C (kg/L) (lbs/gal)	0.98 8.16	ASTM D1475
Flash point	32°C / 90°F	ASTM D93
Recommended Use Level (phr, EEW 190)	87	-

Typical properties are not to be construed as specifications

¹Based on total product weight

CURE PROPERTIES

	FORMULATION	TEST METHOD
Liquid Epoxy Resin (pbw, EEW 190)	100	
Cardolite NX-5110 (pbw)	87	
Mix viscosity @ 25°C (cPs)	2,759	
Gel time, 50 g @ 25°C (min)	40	NTM-15
Thin film dry times, 8 mils (200 micron)		
@ 25°C (77°F) (hrs hard/through)	3.1/4.2	ASTM D5895
@ 5°C (41°F) (hrs hard/through)	9.6/13.1	ASTM D5895
@ 0°C (32°F) (hrs hard/through)	23.5/27.4	ASTM D5895
Film appearance @ 10°C, 92% RH	Clear	Visual

REGULATORY STATUS

Please refer to the material safety data sheet (MSDS). Specific information regarding chemical inventory listing can be obtained from your local sales representative.

SAFETY PRECAUTIONS

Please refer to the material safety data sheet (MSDS). Copies of the MSDS can be requested on the Cardolite website or via your local sales representative.

STABILITY AND STORAGE

Cardolite products may absorb moisture and carbon dioxide when left in open containers, which could result in increased viscosity, discoloration, reduction of reactivity, and/or crystallization of the products. These products should be kept tightly sealed in their original containers when not in use, and stored in a cool, dry place.

CONTACT INFORMATION



<http://www.cardolite.com>

Cardolite Corporation
11 Deer Park Drive
Suite 124
Monmouth Junction, NJ
08852
United States of America

Cardolite Specialty
Chemicals Europe NV
Wijmenstraat 21K / 2
B-9030 Mariakerke (Gent)
Belgium

Cardolite Specialty Chemicals
India LLP
Plot No. IP-1 & IP-2, Mangalore
Special Economic Zone
Bajpe, Mangalore 574 142
India

Cardolite Chemical
Zhuhai Ltd.
1248 Ninth Shihua Road
Gaolan Port Economic Zone
Zhuhai, Guangdong 519050
P.R. China

T: +1-973-344-5015

T: +32 (0) 92658826

T: + 91 (0) 824 2888 300

T: +86-756-726-9066

DISCLAIMER & COPYRIGHT

All statements, technical information and recommendations contained herein are based on tests Cardolite believes to be reliable, but the accuracy or completeness thereof is not guaranteed. Actual test method procedures may differ from listed standards; major differences are noted. Limitation of liability and remedy: Purchase or use of these products constitutes an agreement with seller and manufacturer that, if the product proves to be defective or unsuitable, seller's and manufacturer's liability and the exclusive remedy, regardless of tort or contract theory or of incidental or consequential damages shall be to receive, at seller's or manufacturer's option, an equivalent quantity of replacement product or a refund of the purchase price. This datasheet is copyrighted to Cardolite Corporation and may be reproduced but not altered in any way.