Cardolite® NT-3000 Epoxy Reactive Diluent Technical Datasheet

DESCRIPTION

Cardolite NT-3000 is an aliphatic monoglycidyl ether containing alkyl chains, which are predominately C12 and C14 in length.

TYPICAL PROPERTIES

PROPERTY	SPECIFICATION	Test Method
Appearance	Clear Liquid	Visual
Color (APHA)	≤ 50	ASTM D1544
Viscosity @ 25°C (cPs)	5 - 10	ASTM D2196
Epoxy Equivalent Weight (EEW) ¹	275 - 300	ASTM D1652-97
Moisture content (%)	≤ 0.1	ASTM D4672

¹Based on total product weight

REGULATORY STATUS

Please refer to the material safety data sheet (MSDS). Specific information regarding chemical inventory listing can be obtained from your local sales representative.

SAFETY PRECAUTIONS

Please refer to the material safety data sheet (MSDS). Copies of the MSDS can be requested on the Cardolite website or via your local sales representative.

STABILITY AND STORAGE

Cardolite products may absorb moisture and carbon dioxide when left in open containers, which could result in increased viscosity, discoloration, reduction of reactivity, and/or crystallization of the products. These products should be kept tightly sealed in their original containers when not in use, and stored in a cool, dry place.

CONTACT INFORMATION



http://www.cardolite.com

Cardolite Corporation 11 Deer Park Drive Suite 124 Monmouth Junction, NJ 08852 United States of America Cardolite Specialty Chemicals Europe NV Wijmenstraat 21K / 2 B-9030 Mariakerke (Gent) Belgium Cardolite Specialty Chemicals India LLP Plot No. IP-1 & IP-2, Mangalore Special Economic Zone Bajpe, Mangalore 574 142 India

Cardolite Chemical Zhuhai Ltd. 1248 Ninth Shihua Road Gaolan Port Economic Zone Zhuhai, Guangdong 519050 P.R. China

T: +1-973-344-5015

T: +32 (0) 92658826

T: + 91 (0) 824 2888 300

T: +86-756-726-9066

DISCLAIMER & COPYRIGHT

All statements, technical information and recommendations contained herein are based on tests Cardolite believes to be reliable, but the accuracy or completeness thereof is not guaranteed. Actual test method procedures may differ from listed standards; major differences are noted. Limitation of liability and remedy: Purchase or use of these products constitutes an agreement with seller and manufacturer that, if the product proves to be defective or unsuitable, seller's and manufacturer's liability and the exclusive remedy, regardless of tort or contract theory or of incidental or consequential damages shall be to receive, at seller's or manufacturer's option, an equivalent quantity of replacement product or a refund of the purchase price. This datasheet is copyrighted to Cardolite Corporation and may be reproduced but not altered in any way.

Cardolite Technical Datasheet Issue Date: 8/2017 NT-3000 Copyright © 2007-2017 Cardolite Corporation Page 2