Cardolite® NX-5567 Epoxy Curing Agent Technical Datasheet

DESCRIPTION

Cardolite NX-5567 is a solvent free, low viscosity phenalkamine curing agent designed for epoxy coating applications requiring good chemical resistance. It has excellent rapid cure properties, even at low temperatures and provides good adhesion on wet or otherwise unprepared surfaces. Chemical tank and pipe linings needing to protect against corrosion and either immersion or environmental exposure to various solvents, fuels, lubricants, oils, acids, and bases can benefit from this product's good barrier properties.

PROPERTIES

Property	SPECIFICATION	Test Method
Color (Gardner)	≤ 17	ASTM D1544
Viscosity @ 25°C (cPs)	625 - 1,000	ASTM D2196
Amine Value (mg KOH/g)	496 - 592	ASTM D2074

PROPERTY	TYPICAL VALUE	Test Method
Appearance	Orange brown liquid	Visual
Theoretical Active Hydrogen Equivalent (AHEW) ¹	66	Calculated
Density @ 25°C (kg/L) (lbs/gal)	0.97 - 1.02 8.10 - 8.50	ASTM D1475
Flash point	107°C / 225°F	ASTM D93
Recommended Use Level (phr, EEW 190)	35 - 45	-
Shelf Life (Months)	12	-

Typical properties are not to be construed as specifications

APPLICATIONS

Cardolite NX-5567 is usable in chemical resistant, high solids or solvent free, surface tolerant marine, industrial, and protective coatings and linings. Tank, pipe, secondary containment and structural steel immersed or exposed to chemical environments can benefit from coatings based on this product. Typically used with an epoxy novolac, this curing agent's low viscosity offers good workability, and it can be used for coating applications under cold and humid conditions, even over damp and poorly prepared surfaces. Fast cure and good hardness make it ideal for applications requiring fast return to service or multiple coats in a single day. Its ability to cure over a wide temperature range and non-critical mix ratio can bring formulations broad application latitude for protection from application errors.

ADVANTAGES

- Excellent combination of rapid cure and long pot life at both ambient and low (<5°C/40°F) temperatures
- Continues to chemically crosslink at very low temperatures (<0°C/32°C)
- Very good chemical resistance
- Good adhesion to poorly prepared surfaces
- Moisture tolerant during cure
- Excellent early water resistance
- Good flexibility

- Compatibility with most epoxy resins, solvents and their blends
- Superior corrosion resistance mitigating the need for anticorrosion pigments
- · Low viscosity giving good workability
- Non-critical mix ratio
- No induction time required
- Non-toxic
- Based from natural, renewable, non-food chain raw material feedstock

¹ Based on total product weight

	FORMULATION	Test Method
Liquid Epoxy Resin (pbw, EEW 190)	100	
Cardolite NX-5567 (pbw)	35	
Mix viscosity @ 25°C (cPs)	4,250	
Gel time, 50 g @ 25°C (min)	19.8 - 27.4	NTM-15
Thin film dry times, 8 mils (200 micron)		
@ 25°C (77°F) (hrs hard)	3 / 4	ASTM D5895
@ 5°C (41°F) (hrs hard)	10 / 13	
@ 0°C (32°F) (hrs hard)	15 / 19	
Film appearance @ 10°C, 92% RH	Haze	Visual

REGULATORY STATUS

Please refer to the material safety data sheet (MSDS). Specific information regarding chemical inventory listing can be obtained from your local sales representative.

SAFETY PRECAUTIONS

Please refer to the material safety data sheet (MSDS). Copies of the MSDS can be requested on the Cardolite website or via your local sales representative.

STABILITY AND STORAGE

Cardolite products may absorb moisture and carbon dioxide when left in open containers, which could result in increased viscosity, discoloration, reduction of reactivity, and/or crystallization of the products. These products should be kept tightly sealed in their original containers when not in use, and stored in a cool, dry place.

CONTACT INFORMATION



Cardolite Corporation 140 Wharton Road Bristol, PA 19007 United States of America

Cardolite Specialty Chemicals Europe NV Wiimenstraat 21K / 2 B-9030 Mariakerke (Gent) Belgium

Cardolite Specialty Chemicals India LLP Plot No. IP-1 & IP-2, Mangalore Special Economic Zone Bajpe, Mangalore 574 142 India

T: + 91 (0) 824 2888 300

http://www.cardolite.com

1248 Ninth Shihua Road

Gaolan Port Economic Zone

Zhuhai, Guangdong 519050

Cardolite Chemical

Zhuhai Ltd.

P.R. China

T: +1-800-322-7365 T: +32 (0) 92658826 T: +86-756-726-9066

DISCLAIMER & COPYRIGHT

All statements, technical information and recommendations contained herein are based on tests Cardolite believes to be reliable, but the accuracy or completeness thereof is not guaranteed. Actual test method procedures may differ from listed standards; major differences are noted. Limitation of liability and remedy: Purchase or use of these products constitutes an agreement with seller and manufacturer that, if the product proves to be defective or unsuitable, seller's and manufacturer's liability and the exclusive remedy, regardless of tort or contract theory or of incidental or consequential damages shall be to receive, at seller's or manufacturer's option, an equivalent quantity of replacement product or a refund of the purchase price. This datasheet is copyrighted to Cardolite Corporation and may be reproduced but not altered in any way.

Cardolite Technical Datasheet Issue Date: 9/2021 NX-5567 Page 2