

Cardolite® NX-5620

Epoxy Curing Agent

Composite & Adhesive Applications

DESCRIPTION

Cardolite NX-5620 is a solvent-free, medium viscosity phenalkamine curing agent designed for ambient and low temperature cure with liquid epoxy resins and epoxy based fiber reinforced composites. It is specifically designed to have very good fiber wetting and to be applicable in a variety of different production processes. NX-5620 is characterized by excellent resistance to water, alkali and acid solutions

PROPERTIES

PROPERTY	TYPICAL VALUE	TEST METHOD
Color (Gardner)	≤ 14	ASTM D1544
Viscosity @ 25°C (cPs)	876	ASTM D2196
Amine Value (mg KOH/g)	450 - 510	ASTM D2074
Density @ 25°C (kg/L) (lbs/gal)	0.99 - 1.01 8.18 - 8.43	ASTM D1475

PROPERTY	TYPICAL VALUE	TEST METHOD
Appearance	Light Orange Liquid	Visual
Theoretical Active Hydrogen Equivalent (AHEW) ¹	82	Calculated
Recommended Use Level (phr, EEW 190) ²	40	-

Typical properties are not to be construed as specifications

¹ Based on total product weight

² With Liquid Epoxy Resin (EEW = 190 g/eq)

APPLICATIONS

- Composites based on epoxy chemistry
- Vacuum assisted composite processing
- Resin Transfer Molding
- Wet Lay Up and Lamination
- Construction Adhesives

ADVANTAGES

- Good processability
- Excellent resistance to alkali and acid solutions
- Good reactivity at room temperature
- Moisture tolerant during cure
- Compatible with most epoxy resins, solvents and their blends
- Non-critical mix ratio
- Based from natural, renewable, non-food chain raw material feedstock

TYPICAL HANDLING PROPERTIES

PROPERTIES	TYPICAL VALUE	TEST METHOD
Use Level with Liquid Epoxy Resin (pbw, EEW 190)	40	-
Mix viscosity @ 25°C (cPs)	4,542	ASTM D2196
Mix viscosity @ 40°C (cPs)	980	ASTM D2196
Pot Life, 100 g mix @ 25°C (min)	63	Internal Method ¹
Pot Life, 100 g mix @ 40°C (min)	24	Internal Method ¹
Peak exotherm, 100 g mix @ 25°C (°C)	103	ASTM D2471-99

¹Pot Life is measured when the formulation reaches a limit viscosity of 10,000 cps at the reference temperature.

TYPICAL PERFORMANCE PROPERTIES

PROPERTIES	TYPICAL VALUE ¹	TEST METHOD
Glass transition temperature (°C) ²	102	ASTM 3418-99
Tensile strength (MPa)	53	ASTM D638-10
Tensile modulus (MPa)	2,230	ASTM D638-10
Tensile elongation (%)	4.7	ASTM D638-10
Flexural strength (MPa)	96	ISO 178
Flexural modulus (MPa)	2,405	ISO 178

¹Curing schedule: 4h@RT + 2h@100°C, Base resin: Liquid epoxy (EEW=190)

²DSC scan from 0 to 200°C, 2nd run

CHEMICAL RESISTANCE

CHEMICAL IMMERSION @ 25°C ASTM D543	FORMULATION A	FORMULATION B
Use Level with Liquid Epoxy Resin (pbw, EEW 190)	100	100
Cardolite NX-5620	40	-
JEFFAMINE® D-230 Polyetheramine	-	31

CHEMICALS	FORMULATION A (WEIGHT INCREASE %)			FORMULATION B (WEIGHT INCREASE %)		
	3 days	7 days	14 days	3 days	7 days	14 days
Deionized water	0.30	0.39	0.55	0.37	0.49	0.66
10% sodium hydroxide	0.27	0.43	0.55	0.32	0.48	0.71
3% sulfuric acid	0.45	0.61	0.82	2.77	3.83	5.15
Acetone	5.13	7.94	11.79	Damaged	-	-
Toluene	1.45	2.53	4.15	4.82	7.70	11.63

REGULATORY STATUS

Please refer to the material safety data sheet (MSDS). Specific information regarding chemical inventory listing can be obtained from your local sales representative.

SAFETY PRECAUTIONS

Please refer to the material safety data sheet (MSDS). Copies of the MSDS can be requested on the Cardolite website or via your local sales representative.

STABILITY AND STORAGE

Cardolite products may absorb moisture and carbon dioxide when left in open containers, which could result in increased viscosity, discoloration, reduction of reactivity, and/or crystallization of the products. These products should be kept tightly sealed in their original containers when not in use, and stored in a cool, dry place.

CONTACT INFORMATION



<https://www.cardolite.com>

Cardolite Corporation
140 Wharton Road
Bristol, PA 19007
United States of America

Cardolite Specialty
Chemicals Europe NV
Wijmenstraat 21K / 2
B-9030 Mariakerke (Gent)
Belgium

Cardolite Specialty Chemicals
India LLP
Plot No. IP-1 & IP-2, Mangalore
Special Economic Zone
Bajpe, Mangalore 574 142
India

Cardolite Chemical
Zhuhai Ltd.
1248 Ninth Shihua Road
Gaolan Port Economic Zone
Zhuhai, Guangdong 519050
P.R. China

T: +1-800-322-7365

T: +32 (0) 92658826

T: + 91 (0) 824 2888 300

T: +86-756-726-9066

DISCLAIMER& COPYRIGHT

All statements, technical information and recommendations contained herein are based on tests Cardolite believes to be reliable, but the accuracy or completeness thereof is not guaranteed. Actual test method procedures may differ from listed standards; major differences are noted. Limitation of liability and remedy: Purchase or use of these products constitutes an agreement with seller and manufacturer that, if the product proves to be defective or unsuitable, seller's and manufacturer's liability and the exclusive remedy, regardless of tort or contract theory or of incidental or consequential damages shall be to receive, at seller's or manufacturer's option, an equivalent quantity of replacement product or a refund of the purchase price. This datasheet is copyrighted to Cardolite Corporation and may be reproduced but not altered in any way.