

Cardolite® NC-565

Epoxy Curing Agent

Technical Datasheet

DESCRIPTION

Cardolite NC-565 is a 65% solids, low viscosity, adducted phenalkamine curing agent designed for medium and high solids epoxy coating applications. This curing agent has very fast cure even at low temperatures, and can provide excellent adhesion on difficult substrates, such as an organic zinc primer and degreased galvanized steel. Film quality of coatings using this curing agent is excellent, showing no blush even at low temperatures and high humidity. Like other Cardolite phenalkamines, this curing agent has good adhesion on wet or otherwise unprepared surfaces, and can provide outstanding water resistance and corrosion protection.

PROPERTIES

PROPERTY	SPECIFICATION	TEST METHOD
Color (Gardner)	≤ 16	ASTM D1544
Viscosity @ 25°C (cPs)	300 - 2,300	ASTM D2196
Amine Value (mg KOH/g)	159 - 211	ASTM D2074
Solids (% weight)	63 - 67	ASTM D2369-98

PROPERTY	TYPICAL VALUE	TEST METHOD
Appearance	Orange, brown liquid	Visual
Theoretical Active Hydrogen Equivalent (AHEW) ¹	174	Calculated
Density @ 25°C (kg/L) (lbs/gal)	0.96 - 0.98 7.99 - 8.16	ASTM D1475
Flash point	32°C / 90°F	ASTM D93
Recommended Use Level (phr, EEW 190)	100	-
Shelf Life (Months)	24	-

Typical properties are not to be construed as specifications

¹ Based on total product weight

APPLICATIONS

Cardolite NC-565 is suitable for fast curing medium and high solids surface tolerant marine, industrial, and protective coatings. This product's fast cure and good hardness make it ideal for applications requiring fast return to service or multiple coats over a short period of time. It can be used for coating applications under cold and humid conditions, even over damp and poorly prepared surfaces. Good flexibility and adhesion on various metal/primed substrates make this curing agent especially suitable for primers of marine, transportation, and general industrial equipment. It's ability to cure quickly over a wide temperature range, including below 0°C, combined with a good pot life at room temperature brings coatings based on this curing agent broad application latitude and good workability.

ADVANTAGES

- Excellent combination of rapid cure and long pot-life at both ambient and low (<5°C/40°F) temperatures
- Continues to chemically crosslink at very low temperatures (<0°C/32°F)
- Low viscosity for excellent workability
- Good adhesion to poorly prepared surfaces
- Good adhesion to difficult substrates
- Moisture tolerant during cure
- Excellent water and chemical resistance
- Good flexibility
- Compatible with most epoxy resins, solvents, and their blends
- Superior corrosion resistance mitigating the need for anti-corrosion pigments
- Blush-free surfaces at extreme conditions
- No induction time required
- Based from natural, renewable non-food chain raw material feedstock

CURE PROPERTIES

	FORMULATION	TEST METHOD
Liquid Epoxy Resin (pbw, EEW 190)	100	
Cardolite NC-565 (pbw)	100	
Mix viscosity @ 25°C (cPs)	1,550	
Gel time, 50 g @ 25°C (min)	100	NTM-15
Thin film dry times, 8 mils (200 micron)		
@ 25°C (77°F) (hrs hard/through)	3/4	ASTM D5895
@ 5°C (41°F) (hrs hard/through)	9/12	ASTM D5895
@ 0°C (32°F) (hrs hard/through)	11/14	ASTM D5895
Film appearance @ 10°C, 92% RH	Clear	Visual

REGULATORY STATUS

Please refer to the material safety data sheet (MSDS). Specific information regarding chemical inventory listing can be obtained from your local sales representative.

SAFETY PRECAUTIONS

Please refer to the material safety data sheet (MSDS). Copies of the MSDS can be requested on the Cardolite website or via your local sales representative.

STABILITY AND STORAGE

Cardolite products may absorb moisture and carbon dioxide when left in open containers, which could result in increased viscosity, discoloration, reduction of reactivity, and/or crystallization of the products. These products should be kept tightly sealed in their original containers when not in use, and stored in a cool, dry place.

CONTACT INFORMATION



<http://www.cardolite.com>

Cardolite Corporation
140 Wharton Road
Bristol, PA 19007
United States of America

Cardolite Specialty
Chemicals Europe NV
Wijmenstraat 21K / 2
B-9030 Mariakerke (Gent)
Belgium

Cardolite Specialty Chemicals
India LLP
Plot No. IP-1 & IP-2, Mangalore
Special Economic Zone
Bajpe, Mangalore 574 142
India

Cardolite Chemical
Zhuhai Ltd.
1248 Ninth Shihua Road
Gaolan Port Economic Zone
Zhuhai, Guangdong 519050
P.R. China

T: +1-800-322-7365

T: +32 (0) 92658826

T: + 91 (0) 824 2888 300

T: +86-756-726-9066

DISCLAIMER & COPYRIGHT

All statements, technical information and recommendations contained herein are based on tests Cardolite believes to be reliable, but the accuracy or completeness thereof is not guaranteed. Actual test method procedures may differ from listed standards; major differences are noted. Limitation of liability and remedy: Purchase or use of these products constitutes an agreement with seller and manufacturer that, if the product proves to be defective or unsuitable, seller's and manufacturer's liability and the exclusive remedy, regardless of tort or contract theory or of incidental or consequential damages shall be to receive, at seller's or manufacturer's option, an equivalent quantity of replacement product or a refund of the purchase price. This datasheet is copyrighted to Cardolite Corporation and may be reproduced but not altered in any way.